MC-NE-4 Phenolic epoxy paint

Product description

MC-NE-1 is a highly crosslinked two component phenolic epoxy coating with good heat, chemical and solvent resistance.

Recommended use

Suitable for exposure in high temperature service. The maximum service temperature at dry condition is 230 °C

Recommended film thickness and	spreading rate
--------------------------------	----------------

Film thickness, dry(µm)	40~150
Film thickness, wet(μm)	55.5~208.3
Theoretical spreading rate, m ² /l	18 4.8

Basic characteristics

Dasic characteristics		
Color	white or grey	
Volume Solids, %	72± 2	
Flash Point, °C	30 ± 2	
Density (mix), g/ml	1.59 ± 0.05	
VOC, g/l	320 ± 10	
Water resistance	Excellent	
Abrasion resistance	Good	
Solvent resistance	Excellent	
Chemical resistance	Excellent	

Surface preparation

New steel:

Roughness: using abrasives suitable to achieve medium grade (ISO 8503-2).

Cleanliness: blast cleaning to min. Sa 2 ½ (ISO 8501-1)

Condition during application

The temperature of the substrate should be at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

Application methods

Spray: use airless spray or air spray.

Brush: recommended for precoating or small area coating only, multiple coats may be required to achieve the specified film thickness.

Application data

Mixing agitate component A and component B respectively, and then mixed

thoroughly

Mixing ratio (weight) A:B=8:1

Pot life (23°C) 1 hours (Reduced at higher temperature)

Thinner/Cleaner MC-EX-1

Recommended airless spray parameters

Usage of hinner $0\sim10\%$ (weight)

Pressure at nozele $15\sim20 \text{ MPa} \text{ (about } 150\sim200 \text{ kg/cm}^2\text{)}$.

Nozzle tp $0.53 \sim 0.68 \,\mathrm{mm}$.

Filter Check to ensure that filters are clean.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

Good ventilation (Outdoor exposure or free circulation of air)

Typical film thickness

One coat on top of inert substrate

Substrate temperature, °C	10	23	40
Surface dry, h	12	4	3
Through dry, h	36	10	6
Cured, d	15	7	5
Dry to recoat, minimum, h	36	10	6

The given data must be considered as guidelines only. The actual drying time/ recoat interval may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc.

Typical paint system

MC-NE-1 phenolic epoxy paint

um3×100

Not suitable for application over other primers.

Remarks

When the application temperature is below 10, it is recommended that 10 minutes of induction time is needed after mixing of component A and B.

Storage

Storage conditions are to keep the containers in a cool, dry, well ventilated space and away from source of heat and ignition.

Containers must be kept tightly closed.

Handling

Handle with care.

Packing size

Component A in an 18 litre container and component B in a 5 litre container, or negotiation.

Health and safety

Before and during use of this product, please observe the precautionary notices displayed on the container. Be careful to avoid inhalation and skin contact of paint. Spillage of paint on the skin should immediately be removed with a suitable cleanser, soap and water. Avoid using organic solvent. Eyes should be well flushed with water and then seek medical attention immediately. The product should be used under well-ventilated condition. If using in stagnant condition and narrow place, forced ventilation must be provided, and applicators should take corresponding measures to strengthen personnel protection.

For detailed information on the health and safety and precautions for use of this product, please consult our company.

Statement

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product can be used