
Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

Good ventilation (Outdoor exposure or free circulation of air)

Typical film thickness

One coat on top of inert substrate

Substrate temperature, °C	-5	0	5	10	23
40					
Surface dry, h	12	8	6	4	2
1					
Through dry, h	24	20	18	36	24
12					
Cured, d	14	12	10	7	5
3					
Dry to recoat, minimum, h	24	20	18	36	24
12					

Dry to recoat, maximum*

The given data must be considered as guidelines only. The actual drying time/ recoat interval may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. .

Typical paint system

Epoxy zinc rich primer

60 μm

Epoxy deck coating

2×160μm

Other systems may be formulated, depending on specific condition.

Note

Application method:

- 1、 One coat of epoxy deck paint is applicated in the first and then anti-skid is sprinkled on the first coat before the film dry. The floating anti-skid is swept off in the second day and then epoxy deck paint is coated again.
 - 2、 10~20% of anti-skid is added into epoxy deck paint, then applicated by knife coating.
-

Storage

Storage conditions are to keep the containers in a cool, dry, well ventilated space and away from source of heat and ignition.

Containers must be kept tightly closed.

Handling

Handle with care.

Packing size

Component A in an 18 litre container and component B in a 5 litre container, or negotiation.

Health and safety

Before and during use of this product, please observe the precautionary notices displayed on the container. Be careful to avoid inhalation and skin contact of paint. Spillage of paint on the skin should immediately be removed with a suitable cleanser, soap and water. Avoid using organic solvent. Eyes should be well flushed with water and then seek medical attention immediately. The product should be used under