
MC-FT-1 Modified fluorocarbon topcoat

Product description

MC-FT-1 is a two-component topcoat comprised with modified fluorocarbon resin, weather resistance pigment, curing agent etc.. The cured film exhibits super weatherability, excellent resistance to chemical and fouling and good self-cleaning performance which can withstand the intense changes in offshore climate and sea water splash erosion.

Recommended use

As topcoat suitable for long-term protection of port machinery, offshore drilling platform, steel bridges and other large steel structure under harsh conditions, such as marine and industrial atmosphere exposure.

Recommended film thickness and spreading rate

Film thickness, dry(μm)	30~60
Film thickness, wet(μm)	55.5~111.1
Theoretical spreading rate, m^2/l	18 9

Basic characteristics

Color	Various color
Volume Solids, %	54 \pm 2 (white)
Flash Point, $^{\circ}\text{C}$	27 \pm 2
Density (mix), g/ml	1.22 \pm 0.05(White)
VOC, g/l	485 \pm 10
Gloss	Glossy
Gloss retention	Excellent
Water resistance	Good
Chemical resistance	Good

Surface preparation

Coated surfaces:

Clean, dry and undamaged compatible primer.

Damage areas should be blasted to $\text{Sa}2 \frac{1}{2}$ or power tool cleaning to the standard St3, and primed.

Other surfaces:

The topcoat can be used on other substrates. Please contact our company for more information.

Condition during application

The temperature of the substrate should be at least 3 $^{\circ}\text{C}$ above the dew point of the air. The maximum relative humidity does not exceed 85%. Avoid application in rainy or wet weather. Good ventilation is usually required in confined areas to ensure proper drying.

Application methods

Spray: airless spray or air spray

Application data

Mixing Agitate component A and component B respectively, and then mixed thoroughly

Mixing ratio (weight) A:B=10:1

Pot life (23°C)	5 hours (Reduced at higher temperature)
Thinner/Cleaner	MC-AX-1
Recommended airless spray parameters	
Usage of thinner	0~8% (weight)
Pressure at nozzle	10~15 MPa (about 100~150 kg/cm ²) .
Nozzle tip	0.28~0.43 mm.
Spray angle	40~80°
Filter	Check to ensure that filters are clean.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

Good ventilation (Outdoor exposure or free circulation of air)

Typical film thickness

One coat on top of inert substrate

Substrate temperature, °C	5	10	23	
40				
Surface dry, h	2	1	1/2	
1/4				
Through dry, h	48	24	16	8
Cured, d	14	10	5	3
Dry to recoat, minimum, h	48	24	16	
8				

The surface must be free from any chalking or any other contamination and if necessary, sufficiently roughened prior to application. If recoat interval is longer, all dirt should be first removed with the appropriate detergents, and then the salt on the surface should be rinse with high pressure fresh water.

The given data must be considered as guidelines only. The actual drying time/ recoat interval may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. .

Typical paint system

Epoxy zinc rich primer	70 μm
MIO epoxy coating	130 μm
Modified fluorocarbon topcoat	μm 2×30
Other systems may be formulated, depending on specific circumstances.	

Note

Temperature: when the service temperature is over 100 °C, light discoloration may occur.

Air spray: 20-40% of thinner is recommended with the spraying viscosity of tu-4 cup between 14 to 20 seconds. In some special case, the thinner can be more than 50%, in order to get the best coating appearance.

Film thickness: when application by airless spraying, the dry film thickness of one coat is no more than 60μm.

Storage

Storage conditions are to keep the containers in a cool, dry, well ventilated space and away from source of heat and ignition.

Containers must be kept tightly closed.

Handling

Handle with care.

Packing size

Component A in an 18 litre container and component B in a 4 litre container, or negotiation.

Health and safety

Before and during use of this product, please observe the precautionary notices displayed on the container. Be careful to avoid inhalation and skin contact of paint. Spillage of paint on the skin should immediately be removed with a suitable cleanser, soap and water. Avoid using organic solvent. Eyes should be well flushed with water and then seek medical attention immediately. The product should be used under well-ventilated condition. If using in stagnant condition and narrow place, forced ventilation must be provided, and applicators should take corresponding measures to strengthen personnel protection.

For detailed information on the health and safety and precautions for use of this product, please consult our company.
