
MC-PHE-1 Phenolic anticorrosive paint

Product description

MC-PHE-1 consists of iron oxide red, extender and resin which is based on phenolic resin and drying oil. The cured film exhibits good adhesion and anticorrosive property with good applicability and easy to polish.

Recommended use

Suitable for use in the steel structure on land and vessel above the waterline. It can be used with phenolic and alkyd topcoat.

Recommended film thickness and spreading rate

Film thickness, dry(μm)	30 ~60
Film thickness, wet(μm)	56 ~113
Theoretical spreading rate, m^2/l	18 9

Basic characteristics

Color	iron oxide red or others
Volume Solids, %	54 \pm 2
Flash Point, $^{\circ}\text{C}$	35 \pm 2
Density (mix), g/ml	1.35 \pm 0.05
VOC, g/l	400 \pm 10
Water resistance	fairly good
Chemical resistance	good
Flexibility	good

Surface preparation

Bare steel:

Roughness: using abrasives suitable to achieve medium grade (ISO 8503-2).

Cleanliness: blast cleaning to min. Sa 2 1/2 (ISO 8501-1)

Steel coated shop primer:

Clean, dry, undamaged and recognized shopprimer.

Other surfaces:

The topcoat can be used on other substrates. Please contact our company for more information.

Condition during application

The temperature of the substrate should be at least 3 $^{\circ}\text{C}$ above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

Application methods

Spray: airless spray or air spray

Brush: recommended for precoating or small area coating only, multiple coats may be required to achieve the specified film thickness.

Application data

Thinner/Cleaner	MC-EX-1
Recommended airless spray parameters	
Usage of thinner	0~5% (weight)

Pressure at nozzle	12~15 MPa (about 120~150 kg/cm ²)
Nozzle tip	0.38~0.53 mm.
Spray angle	40~80°
Filter	Check to ensure that filters are clean.

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with: good ventilation (Outdoor exposure or free circulation of air), typical film thickness, one coat on top of inert substrate

Substrate temperature, °C	5	10	23
40			
Surface dry, h	8	6	4
1			
Through dry, h	48	36	24
12			
Dry to recoat, minimum, h	48	36	24
18			

Dry to recoat, maximum*

Clean the surface thoroughly by high pressure fresh water when coating exposed to pollution environmental before recoating

The given data must be considered as guidelines only. The actual drying time/ recoat interval may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc.

Typical paint system

Phenolic anticorrosive paint	2×40 μm
Phenolic topcoat	2×30 μm
Other systems may be formulated, depending on specific condition.	

Storage

Storage conditions are to keep the containers in a cool, dry, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.

Handling

Handle with care.

Packing size

In an 18 litre container, or negotiation.

Health and safety

Before and during use of this product, please observe the precautionary notices displayed on the container. Be careful to avoid inhalation and skin contact of paint. Spillage of paint on the skin should immediately be removed with a suitable cleanser, soap and water. Avoid using organic solvent. Eyes should be well flushed with water and then seek medical attention immediately. The product should be used under well-ventilated condition. If using in stagnant condition and narrow place, forced ventilation must be provided, and applicators should take corresponding measures to strengthen personnel protection.