

---

## MC-C2-1 Chlorinated rubber topcoat

### Product description

MC-C2-1 is a one-component anticorrosive topcoat based on chlorinated rubber. The paint forms a tough film with excellent resistance to water, weatherability and chemicals.

---

### Recommended use

As topcoat suitable for use on the ship, container, port machinery, chemical equipment, steel structure and concrete in moderately to severely corrosive environment. The maximum service temperature at dry condition is 60°C.

---

### Recommended film thickness and spreading rate

Film thickness, dry( $\mu\text{m}$ )	30~80
Film thickness, wet( $\mu\text{m}$ )	63.8~170
Theoretical spreading rate, $\text{m}^2/\text{l}$	15.7 ~5.9

---

### Basic characteristics

Color	Various color
Volume Solids, %	47± 2
Flash Point, °C	29 ± 2
Density (mix), g/ml	1.15±0.05
VOC, g/l	510 ± 10
Gloss	Glossy/matt
Water resistance	Good
Chemical resistance	Good

---

### Surface preparation

#### Coated surfaces:

Clean, dry and undamaged compatible primer.

#### Other surfaces:

The topcoat can be used on other substrates. Please contact our company for more information.

---

### Condition during application

The preceding coat should be completely dry. The temperature of the substrate should be at least 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate. Good ventilation is usually required in confined areas to ensure proper drying.

---

### Application methods

Spray: airless spray or air spray

Brush: recommended for precoating or small area coating only, multiple coats may be required to achieve the specified film thickness.

---

### Application data

Mixing ratio (weight)	one pack(ready to use)
Thinner/Cleaner	MC-CX-1
Recommended airless spray parameters	
Usage of thinner	0~10% (weight)
Pressure at nozzle	15~20 MPa (about 150~200 $\text{kg}/\text{cm}^2$ ) .

---

Nozzle tip	0.4~0.5mm.
Spray angle	40~80°
Filter	Check to ensure that filters are clean.

---

### **Drying time**

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

Good ventilation (Outdoor exposure or free circulation of air)

Typical film thickness

One coat on top of inert substrate

Substrate temperature, °C	5	10	23	40
Surface dry, h	5	3	1	0.5
Through dry, h	12	8	6	3
Dry to recoat, minimum, h	12	8	6	3

The given data must be considered as guidelines only. The actual drying time/ recoat interval may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. .

### **Typical paint system**

Epoxy primer	70µm
Chlorinated rubber topcoat	2×50 µm

### **Other available preceding paint system**

Chlorinated rubber anticorrosive paint, epoxy coal-tar paint.

Other systems may be formulated, depending on specific condition.

### **Storage**

Storage conditions are to keep the containers in a cool, dry, well ventilated space and away from source of heat and ignition.

Containers must be kept tightly closed.

### **Handling**

Handle with care.

### **Packing size**

In an 18 litre container, or negotiation.

### **Health and safety**

Before and during use of this product, please observe the precautionary notices displayed on the container. Be careful to avoid inhalation and skin contact of paint. Spillage of paint on the skin should immediately be removed with a suitable cleanser, soap and water. Avoid using organic solvent. Eyes should be well flushed with water and then seek medical attention immediately. The product should be used under well-ventilated condition. If using in stagnant condition and narrow place, forced ventilation must be provided, and applicators should take corresponding measures to strengthen personnel protection.

**For detailed information on the health and safety and precautions for use of this product, please consult our company.**

---